


# Coatings Certification: Tnemec 140 2 Part Polyamidoamine Epoxy

 <b>POTA-POX® PLUS</b>		PRODUCT DATA SHEET
<b>SERIES N140</b>		
<b>PRODUCT PROFILE</b>		
<b>GENERIC DESCRIPTION</b>	Polyamidoamine Epoxy	
<b>COMMON USAGE</b>	Innovative potable water coating which offers high-build edge protection and allows for application at a wide range of temperatures (down to 35°F or 2°C with 44-700 Accelerator). For use on the interior and exterior of steel or concrete tanks, reservoirs, pipes, valves, pumps, and equipment in potable water service.	
<b>COLORS</b>	1211 Red, 1255 Beige, 00WH Tnemec White, 15BL Tank White, 35GR Black and 39BL Delft Blue. <b>Note:</b> Epoxies chalk with extended exposure to sunlight. Lack of ventilation, incomplete mixing, miscatalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial stages of curing may cause yellowing to occur.	
<b>SPECIAL QUALIFICATIONS</b>	<p>Certified by <b>NSF International</b> in accordance with <b>NSF/ANSI/CAN Std. 61</b> and the extraction requirements of <b>NSF/ANSI/CAN 600</b>. <b>Note:</b> Series N140 is an NSF-approved primer, stripe coat, and intermediate coat for applications on the interior of steel tanks; Series N140 is an NSF-approved primer and finish coat for applications on pumps, valves, fittings, and mechanical devices. Reference Tnemec's certified product listing at <a href="http://www.nsf.org">www.nsf.org</a> for additional details.</p> <p>Conforms to <b>AWWA C210</b> (without 44-700). Contact your Tnemec representative for systems and additional information.</p> <p>A two-coat and three-coat system of Series N140 meets the requirements of <b>AWWA C550</b> Protective Interior Coatings for Valves and Hydrants.</p>	
<b>COATING SYSTEM</b>		
<b>SURFACER/FILLER/PATCHER</b>	Series 215, 217, 218	
<b>PRIMERS</b>	Self-priming, Series 22, 91-H <sub>2</sub> O, 94-H <sub>2</sub> O, 98-H <sub>2</sub> O, L140, L140F, N140F	
<b>TOPCOATS</b>	<p><b>Interior:</b> Series 21, 22, FC22, L140, L140F, N140, N140F, 264, 265, 406.</p> <p><b>Exterior:</b> Series 22, 27, 66, L69, L69F, N69, N69F, V69, V69F, 73, 118, L140, L140F, N140, N140F, 156, 157, 161, 180, 181, 700, V700, 701, V701, 1026, 1028, 1029, 1077, 1078, 1078V, 1080, 1081, 1094, 1095, 1096, 1224. <b>Note:</b> When topcoating with Series 700, V700, 701, or V701, an intermediate coat of Series 73, 1095 or 1096 is required. <b>Note:</b> The following recoat times apply for Series N140: Immersion Service—Surface must be scarified by blasting with fine abrasive after 60 days. Atmospheric Service—After 60 days, scarification or an epoxy tie-coat is required. <b>Note:</b> When topcoating with Series 406, recoat times will vary with temperature. Reference the Series 406 product data sheet for specific recoat times. Contact your Tnemec representative for specific recommendations.</p>	
<b>SURFACE PREPARATION</b>		
<b>STEEL</b>	<p><b>Immersion Service:</b> SSPC-SP10/NACE 2 Near-White Blast Cleaning or ISO Sa 2 1/2 Very Thorough Blast Cleaning with a minimum angular anchor profile of 1.5 mils.</p> <p><b>Non-Immersion Service:</b> SSPC-SP6/NACE 3 Commercial Blast Cleaning or ISO Sa 2 Thorough Blast Cleaning with a minimum angular anchor profile of 1.5 mils. <b>Note:</b> Commercial Blast Cleaning generally produces the best coating performance for this exposure. If conditions will not permit this, in moderate exposures Series N140 may be applied to SSPC-SP2 or SP3 Hand or Power Tool Cleaned surfaces (SSPC Rust Grade Condition C).</p>	
<b>CAST/DUCTILE IRON</b>	All external surfaces of ductile iron pipe and fittings shall be delivered to the application facility without asphalt or any other protective lining on the exterior surface. All oils, small deposits of asphalt paint, grease, and soluble deposits should be removed and uniformly abrasive blasted using angular abrasive in accordance with NAFI 500-03-04: External Pipe Surface condition. When viewed without magnification, the exterior surfaces shall be free of all visible dirt, dust, loose annealing oxide, rust, mold coating and other foreign matter. Any area where rust reappears before application shall be reblasted. The surface shall contain a minimum angular anchor profile of 1.5 mils (38.1 microns) (Reference NACE RP0287 or ASTM D 4417, Method C).	
<b>CONCRETE</b>	Allow new cast-in-place concrete to cure a minimum of 28 days at 75°F (24°C). Verify concrete dryness in accordance with ASTM F 1869 "Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride" (moisture vapor transmission should not exceed three pounds per 1,000 square feet in a 24 hour period), F 2170 "Standard Test Method for Determining Relative Humidity in Concrete using in situ Probes" (relative humidity should not exceed 80%), or D 4263 "Standard Test Method for Indicating Moisture in Concrete by the Plastic Sheet Method" (no moisture present). Prepare concrete surfaces in accordance with NACE No. 6/SSPC-SP13 Joint Surface Preparation Standards and ICRI Technical Guidelines. Abrasive blast, shot-blast, water jet or mechanically abrade concrete surfaces to remove laitance, curing compounds, hardeners, sealers and other contaminants and to provide an ICRI-CSP 2-3 surface profile. Large cracks, voids and other surface imperfections should be filled with a recommended filler or surfacer.	
<b>PRIMED SURFACES</b>	<b>Immersion Service:</b> Scarify the Series N140 prime coat by brush-blasting with fine abrasive before topcoating if: (a) the Series N140 prime coat has been in exterior exposure for 60 days or longer and Series 66, L69, L69F, N69, N69F, V69, V69F, L140, L140F, N140, N140F, or 161 is the specified topcoat; (b) the Series N140 prime coat has been in exterior exposure for 7 days or longer and Series 264 or 265 is the specified topcoat.	
<b>ALL SURFACES</b>	Must be clean, dry and free of oil, grease and other contaminants.	

© May 15, 2023 by Tnemec Company, Inc.

Published technical data and instructions are subject to change without notice. The online catalog at [www.tnemec.com](http://www.tnemec.com) should be referenced for the most current technical data and instructions or you may contact your Tnemec representative for current technical data and instructions.

PDSN140 Page 1 of 3



SHEET

Coatings Certification: Tnemec 140- 1 of 3

DOC. NO.

D-TNEMEC140CERT-r0

# Coatings Certification: Tnemec 140 2 Part Polyamidoamine Epoxy

PRODUCT DATA SHEET

## POTA-POX® PLUS | SERIES N140

### TECHNICAL DATA

<b>VOLUME SOLIDS</b>	67.0 ± 2.0% (mixed—A, B & 44-700 Epoxy Accelerator) †																								
<b>RECOMMENDED DFT</b>	2.0 to 10.0 mils (50 to 225 microns) per coat. <b>Note:</b> Reference the NSF website at <a href="http://www.nsf.org">www.nsf.org</a> for details on the maximum allowable DFT. <b>Note:</b> The number of coats and thickness requirements will vary with substrate, application method and exposure. Contact your Tnemec representative.																								
<b>CURING TIME AT 5 MILS DFT</b>	Without 44-700 Accelerator:																								
	<table border="1"> <thead> <tr> <th>Temperature</th> <th>To Handle</th> <th>To Recoat</th> <th>Immersion</th> </tr> </thead> <tbody> <tr> <td>90°F (32°C)</td> <td>5 hours</td> <td>7 hours</td> <td>7 days</td> </tr> <tr> <td>80°F (27°C)</td> <td>7 hours</td> <td>9 hours</td> <td>7 days</td> </tr> <tr> <td>70°F (21°C)</td> <td>9 hours</td> <td>12 hours</td> <td>7 days</td> </tr> <tr> <td>60°F (16°C)</td> <td>16 hours</td> <td>22 hours</td> <td>9 to 12 days</td> </tr> <tr> <td>50°F (10°C)</td> <td>24 hours</td> <td>32 hours</td> <td>12 to 14 days</td> </tr> </tbody> </table>	Temperature	To Handle	To Recoat	Immersion	90°F (32°C)	5 hours	7 hours	7 days	80°F (27°C)	7 hours	9 hours	7 days	70°F (21°C)	9 hours	12 hours	7 days	60°F (16°C)	16 hours	22 hours	9 to 12 days	50°F (10°C)	24 hours	32 hours	12 to 14 days
Temperature	To Handle	To Recoat	Immersion																						
90°F (32°C)	5 hours	7 hours	7 days																						
80°F (27°C)	7 hours	9 hours	7 days																						
70°F (21°C)	9 hours	12 hours	7 days																						
60°F (16°C)	16 hours	22 hours	9 to 12 days																						
50°F (10°C)	24 hours	32 hours	12 to 14 days																						
	Curing time varies with surface temperature, air movement, humidity and film thickness. Refer to product listing on <a href="http://www.nsf.org">www.nsf.org</a> for specific potable water return to service information. <b>Ventilation:</b> When used in enclosed areas, provide adequate ventilation during application and cure. <b>Note:</b> For faster curing and low temperature applications, add No. 44-700 Epoxy Accelerator, see separate product data sheet for cure information.																								
<b>VOLATILE ORGANIC COMPOUNDS</b>	<b>Unthinned:</b> 2.4 lbs/gallon (285 grams/litre) <b>Thinned 5% (No. 60 Thinner):</b> 2.6 lbs/gallon (311 grams/litre) <b>Thinned 10% (No. 4 Thinner):</b> 2.8 lbs/gallon (334 grams/litre) †																								
<b>HAPS</b>	<b>Unthinned:</b> 2.4 lbs/gal solids <b>Thinned 5% (No. 60 Thinner):</b> 2.4 lbs/gal solids <b>Thinned 10% (No. 4 Thinner):</b> 3.3 lbs/gal solids																								
<b>THEORETICAL COVERAGE</b>	1,070 mil sq ft/gal (27.2 m <sup>2</sup> /L at 25 microns). See APPLICATION for coverage rates. †																								
<b>NUMBER OF COMPONENTS</b>	Two: Part A (amine) and Part B (epoxy) — One (Part A) to one (Part B) by volume.																								
<b>PACKAGING</b>	<table border="1"> <thead> <tr> <th></th> <th>Part A</th> <th>Part B</th> <th>Yield (mixed)</th> </tr> </thead> <tbody> <tr> <td>Large Kit</td> <td>5 gallon pail</td> <td>5 gallon pail</td> <td>10 gallons (37.9 L)</td> </tr> <tr> <td>Small Kit</td> <td>1 gallon can</td> <td>1 gallon can</td> <td>2 gallons (7.6 L)</td> </tr> </tbody> </table>		Part A	Part B	Yield (mixed)	Large Kit	5 gallon pail	5 gallon pail	10 gallons (37.9 L)	Small Kit	1 gallon can	1 gallon can	2 gallons (7.6 L)												
	Part A	Part B	Yield (mixed)																						
Large Kit	5 gallon pail	5 gallon pail	10 gallons (37.9 L)																						
Small Kit	1 gallon can	1 gallon can	2 gallons (7.6 L)																						
	Reference 44-700 Epoxy Accelerator product data sheet for its packaging information.																								
<b>NET WEIGHT PER GALLON</b>	12.66 ± 0.25 lbs (5.82 ± 0.11 kg) (mixed) †																								
<b>STORAGE TEMPERATURE</b>	Minimum 20°F (-7°C) Maximum 110°F (43°C)																								
<b>TEMPERATURE RESISTANCE</b>	(Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)																								
<b>SHELF LIFE</b>	Part A: 24 months; Part B: 12 months at recommended storage temperature.																								
<b>FLASH POINT - SETA</b>	Part A: 82°F (28°C) Part B: 80°F (27°C) 44-700: None																								
<b>HEALTH &amp; SAFETY</b>	Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product. <b>Keep out of reach of children.</b>																								

### APPLICATION

<b>COVERAGE RATES</b>	<table border="1"> <thead> <tr> <th></th> <th>Dry Mils (Microns)</th> <th>Wet Mils (Microns)</th> <th>Sq Ft/Gal (m<sup>2</sup>/Gal)</th> </tr> </thead> <tbody> <tr> <td>Suggested</td> <td>6.0 (150)</td> <td>9.0 (230)</td> <td>179 (16.6)</td> </tr> <tr> <td>Minimum</td> <td>2.0 (50)</td> <td>3.0 (75)</td> <td>537 (49.9)</td> </tr> <tr> <td>Maximum</td> <td>10.0 (225)</td> <td>15.0 (375)</td> <td>107 (10.0)</td> </tr> </tbody> </table>		Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m <sup>2</sup> /Gal)	Suggested	6.0 (150)	9.0 (230)	179 (16.6)	Minimum	2.0 (50)	3.0 (75)	537 (49.9)	Maximum	10.0 (225)	15.0 (375)	107 (10.0)
	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m <sup>2</sup> /Gal)														
Suggested	6.0 (150)	9.0 (230)	179 (16.6)														
Minimum	2.0 (50)	3.0 (75)	537 (49.9)														
Maximum	10.0 (225)	15.0 (375)	107 (10.0)														
	<b>Note:</b> Roller or brush application requires two or more coats to obtain recommended film thickness. Allow for overspray and surface irregularities. Wet film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. Reference the NSF website at <a href="http://www.nsf.org">www.nsf.org</a> for details on the maximum allowable DFT. †																
<b>MIXING</b>	Start with equal amounts of Series N140 Parts A and B. Power mix contents of each container separately, making sure no pigment remains on the bottom. Pour a measured amount of Part B into a clean container large enough to hold both components. If Series 44-700 is not being used, proceed with mixing and add an equal volume of Part A to Part B while under agitation. Continue agitation until the two components are thoroughly mixed. <b>Note:</b> Both components must be above 50°F (10°C) prior to mixing. For optimum mixing and application properties, the material should be above 60°F (16°C).  If using Series 44-700 accelerator, slowly add four (4) fluid ounces of 44-700 per gallon to Series N140 Part A material while under agitation and proceed with adding Part B. <b>Note:</b> The use of more than the recommended amount of 44-700 will adversely affect performance.																
<b>THINNING</b>	Thin by volume and thoroughly mix. Failure to thoroughly mix the Part A and Part B components prior to thinning can affect product's gloss and performance. Do not use mixed material beyond pot life limits. <b>Note:</b> For application of the unaccelerated version to surfaces between 50°F to 60°F (10°C to 16°C) or the accelerated version to surfaces between 35°F to 50°F (2°C to 10°C), allow mixed material to stand 30 minutes and restir before using.  Use No. 4 or No. 60 Thinner. For air spray, thin up to 10% or 3/4 pint (380 mL) per gallon with No. 4 Thinner or thin up to 5% or 1/4 pint (190 mL) per gallon with No. 60 Thinner. For airless spray, roller, or brush, thin up to 5% or 1/4 pint (190 mL) per gallon. <b>Caution: Series N140 NSF certification is based on thinning with No. 4 Thinner for tanks and No. 60 Thinner for pumps, valves, fittings, and mechanical devices.</b> Use of any other thinner voids NSF/ANSI/CAN Std. 61 certification.																
<b>POT LIFE</b>	Without 44-700 6 hours at 50°F (10°C) 4 hours at 75°F (24°C) 1 hour at 100°F (38°C) With 44-700 2 hours at 50°F (10°C) 1 hour at 75°F (24°C) 30 minutes at 100°F (38°C)																

© May 15, 2023 by Tnemec Company, Inc.

PDSN140 Page 2 of 3



SHEET

Coatings Certification: Tnemec 140- 2 of 3

DOC. NO.

D-TNEMEC140CERT-r0

# Coatings Certification: Tnemec 140 2 Part Polyamidoamine Epoxy

PRODUCT DATA SHEET

## POTA-POX® PLUS | SERIES N140

**SPRAY LIFE**  
**APPLICATION EQUIPMENT**

Without 44-700: 1 hour at 77°F (25°C) With 44-700: 30 minutes at 75°F (24°C)  
**Note:** Spray application after listed times will adversely affect ability to achieve recommended dry film thickness.

**Air Spray**

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss JGA	E	765 or 704	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	50-80 psi (3.4-5.5 bar)	10-20 psi (0.7-1.4 bar)

**Airless Spray**

Tip Orifice	Atomizing Pressure	Mat'l Hose ID	Manifold Filter
0.015"-0.019" (380-485 microns)	3000-4800 psi (207-330 bar)	1/4" or 3/8" (6.4 or 9.5 mm)	60 mesh (250 microns)

Low temperatures or longer hoses require higher pot pressure. Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.  
**Roller:** Use 3/8" or 1/2" (9.5 mm to 12.7 mm) synthetic woven nap roller cover. Use longer nap to obtain penetration on rough or porous surfaces.  
**Brush:** Recommended for small areas only. Use high quality natural or synthetic bristle brushes.

**SURFACE TEMPERATURE**

Without 44-700: Min. 50°F (10°C), Max. 135°F (57°C) With 44-700: Min. 35°F (2°C), Max. 135°F (57°C)  
The surface should be dry and at least 5°F (3°C) above the dew point. Coating will not cure below minimum surface temperature.

**CLEANUP**

Flush and clean all equipment immediately after use with the recommended thinner or MEK.

† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.

Tnemec Company, Inc. 6800 Corporate Drive Kansas City, Missouri 64120-1372 +1 816-483-3400 www.tnemec.com

© May 15, 2023 by Tnemec Company, Inc.

PDSN140 Page 3 of 3



SHEET

Coatings Certification: Tnemec 140- 3 of 3

DOC. NO.

D-TNEMEC140CERT-r0